

I. RESULTS OF ANALYSIS

Before loading operations representative samples had taken by us at stock pile and the samples submitted to our laboratory for analysis, and the results of analysis as follows :

Parameter	Unit	Results	Method
-Total Moisture	%	17.82	ASTM D 1762-84
- Moisture in Analysis	%, db	2.35	ASTM D 1762-84
- Ash Content	%, db	2.46	ASTM D 1762-84
- Volatile Matter	%, db	77.92	ASTM D 1762-84
- Fixed Carbon	%, db	17.27	ASTM D 1762-84
-Total Sulfur	%, adb	0.03	ASTM D 4239-14
-Gross Calorific Value	kcal/kg, db	4248	ASTM D 5865-13
-Foreign Matter	%	0.73	Gravimetric

*Sesuai Permintaan

ASTM : American Standar Testing and Material